

BW COAT 3641A

Rust Protection of Cavity Part for all vehicle

Description	BW COAT 3641A is the wax type of Rust Protective for cavity area for all kind of car. The product is designed to have excellent rust protection property to extend the car body's life. It can apply at OEM industry and																						
Benefits	1. Good anti-sag property at high temperature(40 ~ 50℃) process. 2. To extend the car body's life due to excellent rust protection property. 3. Excellent film flexibility under extreme low temperature condition(-35℃)																						
Typical properties	<table><tr><th>Items</th><th>Results</th><th>Test method</th></tr><tr><td>Appearance</td><td>Light Yellow Opaque,Liquid</td><td>To see</td></tr><tr><td>Type of film</td><td>Waxy</td><td>-</td></tr><tr><td>Specific Gravity (20℃)</td><td>0.85</td><td>JIS K 5400</td></tr><tr><td>Flesh Point(℃)</td><td>42</td><td>KS M 2010</td></tr><tr><td>Viscosity(20℃,20rpm,cPs)</td><td>3000</td><td>JIS K 5400</td></tr><tr><td>Non-volatile matter (wt, %)</td><td>62.0</td><td>KS M 2525</td></tr></table> * Above test results are new fluid's typical properties, can be changed by quality improvement.		Items	Results	Test method	Appearance	Light Yellow Opaque,Liquid	To see	Type of film	Waxy	-	Specific Gravity (20℃)	0.85	JIS K 5400	Flesh Point(℃)	42	KS M 2010	Viscosity(20℃,20rpm,cPs)	3000	JIS K 5400	Non-volatile matter (wt, %)	62.0	KS M 2525
Items	Results	Test method																					
Appearance	Light Yellow Opaque,Liquid	To see																					
Type of film	Waxy	-																					
Specific Gravity (20℃)	0.85	JIS K 5400																					
Flesh Point(℃)	42	KS M 2010																					
Viscosity(20℃,20rpm,cPs)	3000	JIS K 5400																					
Non-volatile matter (wt, %)	62.0	KS M 2525																					
Application	It can be used for cavity and parts to protect rust of all kind of car including passenger car , truck and bus.																						
Term of validity	12 months from the date of manufacture at sealed state, 0 to 40℃.																						
Safety information	Refer to the our MSDS for safety information																						

The information contained and the recommendations made in this data sheet are based upon data collected and believed by us to be correct. However, no guarantee or warranty of any kind, expressed or implied, is made herein with respect to the merchandise described and we assume no responsibility for the results or the use there of.